

THERMAX® LIGHT DUTY (LD)
INSULATION/FINISH BOARD (TF600)



Build On Our Knowledge™



**Designed For Exposed
Interior Applications to
Withstand Light Impact**

Thermax[®] LIGHT DUTY (LD)

Insulation/Finish Board

Thermax LD

Thermax Light Duty (LD) Insulation / Finish Board is a glass fiber reinforced polyisocyanurate foam core faced with nominal 1.25 mil embossed white acrylic coated aluminum on one side and 1.25 mil embossed aluminum on the other side.

Applications

THERMAX LD BOARD IS INTENDED AS AN INSULATION AND INTERIOR FINISH SYSTEM FOR METAL, WOOD POST FRAME AND CONCRETE OR MASONRY BUILDINGS in manufacturing, mercantile, cold storage, warehouse, agricultural and other applications, as governed by building codes. Thermax LD is the most economically priced in the Thermax Insulation / Finish Board family and provides excellent aesthetics where high durability is not critical.



Thermax Light Duty (LD) Insulation/Finish Board FEATURES:

- HIGH R-VALUES
- ATTRACTIVE SURFACE
- DURABLE FINISH

1.25 MIL Embossed Aluminum with White Acrylic Surface Finish

- ▼ Thermax LD with the tough white acrylic surface **can be pressure washed up to 1000 psi assuring moderate high pressure cleaning.**
- ▼ Thermax LD with the white embossed surface has a light reflectance of 65% **which helps reduce light energy cost and enhances the work environment.**
- ▼ The acrylic coated surface helps protect the product from long term degradation in harsh interior environments **which reduces long term replacement costs.**
- ▼ The 1.25 mil aluminum faced product has resistance to light impact **which helps reduce product damage and replacement costs.**

Strength (SPANABILITY)

Thermax LD has an allowable clear span of 5 feet (1" or greater) over purlins and 8 feet (1" and greater) over girts **which saves on installation time and design cost.**

Low Perm Product with Joint Closure System

Thermax LD has an extremely low perm rating (vapor flow) of less than 0.03 and must be installed with one of the following joint closure systems:

- ▼ Matching Thermax white coated 2 mil aluminum tape adhered over the butt joint. Joint quality: **Good**
- ▼ Factory produced ship lap joint used with sealant. Joint quality: **Better**
- ▼ Thermax white (PVC) Clip Strip Joint Closure system used with sealant. Joint quality: **Best**

The low perm product / joint systems prevent moisture condensation within and behind the insulation and minimize structural wood decay, metal corrosion and condensation (rain) inside the structure.

Design Flexibility

Thermax LD comes in a range of thicknesses and lengths up to 30 feet. **This allows for sizing to meet specific R-value requirements and to reduce installed costs.**

Assured Thermal Performance

Thermax LD is continually tested at the NAHB Research Center to verify thermal performance. Accordingly, **Celotex offers a 15 year limited warranty on R-value thermal resistance.**

Fire and Wind Uplift Performance

Fire Performance & Insurance

Thermax LD is Classified by Underwriters Laboratories Inc. for the Insulated Wall-Ceiling Constructions Category and the Interior Building Constructions Category. **These classifications are recognized by the Insurance Services Office (ISO) and other insurance authorities as a basis to obtain the lowest possible insurance rates in insulated structures.**

Thermax LD is also Approved by Factory Mutual Research Corporation as Class 1 Wall and Ceiling panels for use as an exposed insulation / interior finish when installed as described in the current edition of the FMRC Approval Guide. **This assures a basis to gain the lowest possible insurance rates through the Factory Mutual System.**

Wind Uplift & Insurance

Thermax LD is Classified by Underwriters Laboratories Inc. for Wind Uplift Resistance and is shown to be equal to or superior to glass fiber insulation in wind uplift performance. Moreover, Thermax LD is listed in many UL roof deck construction numbers in the UL Roofing Materials and Systems Directory. **These classifications will allow for lower insurance premiums.**

United States Department of Agriculture (USDA) & Food and Drug Administration (FDA)

Thermax Light Duty meets the USDA/FSIS guideline requirements for use in federally inspected food processing establishments. **Based on the aforementioned Light Duty can be used in food processing facilities where the product does not come in contact with food.**

Installation

Wall Application - Attached to Concrete or Masonry

Thermax Light Duty (LD) Insulation / Finish Board system can be installed **EXPOSED** to the interior of masonry or concrete walls using the Thermax PVC Interlock Joint Closure System placed 4'-0" o.c. Wood or metal furring may also be used.

Roof / Ceiling Application - Attached to Purlin or Truss

Thermax Light Duty (LD) Insulation/Finish Board can be installed **EXPOSED** to the interior on the inside or outside of wood or metal purlins or trusses.

Wall Application - Attached to Girts

Thermax Light Duty (LD) Insulation/Finish Board can be installed **EXPOSED** to the interior on the inside or outside of wood or metal girts.

Thermax Light Duty Technical Data

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Value
Density (pcf)	ASTM D 1622	Nominal 2
Water Vapor Transmission as Permeance, In Perms	ASTM E 96 (Desiccant Method)	Less than 0.03
Modulus of Elasticity (1" product, MD/TD, PSI)	ASTM C 203	2500 / 3000
Modulus of Rupture (1" product, MD/TD, PSI)	ASTM C 203	74 / 74
Impact (lbs max)	ASTM D 1037 (Janka Ball)	8
Light Reflectance (%) Northern Light Incandescent Light Fluorescent Light	Visual Light Spectrophotometer	65 65 65
Operating Temp Range (°F)	—	-100 to +250
Liquid Water Absorption as Percent Increase by volume	ASTM C 209, 24-Hr Results	0.3 Max
Compressive Strength in Thickness Direction, psi	ASTM D 1621	25

PRODUCT THICKNESS AND STABILIZED R-VALUE*

Nominal Board Thickness (inches) (mm)	1/2" (12.7)	3/4" (19.1)	1" (25.4)	1 1/4" (31.8)	1 1/2" (38.1)	1 3/4" (44.5)
R-Value @ 40°F mean temp.	4	6	8	10	12	14
R-Value @ 75°F mean temp.	3.6	5.4	7.2	9	10.8	12.6

Nominal Board Thickness (inches) (mm)	2" (50.8)	2 1/4" (57.2)	2 1/2" (63.5)	2 3/4" (69.8)	3" (76.2)
R-Value @ 40°F mean temp.	16	18	20	22	24
R-Value @ 75°F mean temp.	14.4	16.2	18	19.8	21.6

Stabilized R-Values were determined by ASTM C 518 in accordance with the procedures in Federal Specification HH F-1972, ASTM C 1289 and the State of California Insulation and Quality Standards.

* To obtain RSI, multiply R-value x 0.1761.

Washability Requirement

Light Duty can be pressure washed up to 1000 psi with any spray tip greater than 15 degrees with a minimum of 3 feet from the surface.

CAUTION: Prolonged pressure washing at the board joints will cause the facer to disbond from the insulation board. Always point spray nozzle at the surface no closer than the minimum distance.

Compliances

- ICC:** International One- and Two Family Dwelling Code Sect. 317. International Building Code Section 2603
- BOCA:** Building Officials and Code Administrators International, Inc. Research Report No. 98-25 and National Building Code Sect. 2603.0.
- ICBO:** International Conference of Building Officials, Evaluation Report No. 3223 and Uniform Building Code, Sect. 2602.
- SBCCI:** Southern Building Code Congress International, Evaluation Report No. 9574 C and Standard Building Code, Sect. 2603.

Performance Tests

FACTORY MUTUAL (FMRC Standard 4880)

Subject to the conditions of Approval as Class 1 wall and ceiling panels when installed as described in the current edition of the FMRC Approval Guide. FACTORY MUTUAL SYSTEM APPROVED.

UNDERWRITERS LABORATORIES, INC.

Classified Foamed Plastic - for insulated wall-ceiling constructions as to fire damageability only (UL 1040); for interior building constructions with regard to flame propagation and damageability under specified room fire conditions only (UL 1715, UBC 26-3).

SURFACE BURNING CHARACTERISTICS (UL 723, UBC 8-1, ASTM E 84)

	Core Materials				
	1/2 in. Thick Maximum	2 in. Thick Maximum	4 1/4 in. Thick Maximum		
Flame Spread	20	20	25		
Smoke Developed	35	85	130-185		
	Finished Faced Boards†				
	1/2 in. Thick Maximum	1 in. Thick Maximum	2 in. Thick Maximum	3 in. Thick Maximum	4 1/4 in. Thick Maximum
Flame Spread	20	20	20	20	20
Smoke Developed	60	80	120	140	125-190

† Installed in a thickness, or stored in effective thicknesses as indicated for a density of 1.6 to 2.0 lb/ft.³

The manufacturer makes the following statement. These numerical ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

ASSURED THERMAL PROPERTIES

Thermax LD carries the NAHB Research Center, Inc. label verifying insulating value and other product physical properties.

UNDERWRITERS LABORATORIES INC. WIND UPLIFT CLASSIFICATION (UL 580)

Thermax Light Duty (LD) in thicknesses of 1" through 4 1/4" has been shown to be equal or superior to glass fiber insulation in wind uplift performance and bears the following Underwriters Laboratories Inc. Wind Uplift Classification.

Thermax foil-faced products in thicknesses from 1" through 4" may be substituted for glass fiber batts or blankets in any through-fastened metal roof deck construction classified by UL for wind uplift resistance without changing the specific classification. Refer to UL Roofing Materials and Systems Directory (TGKX and TJBX Product Category Codes) for details.

Classified as Roof Deck Construction Materials As To Wind Uplift Resistance Only Class 60 As Shown By Construction NOS. 26, 83A, 115, 127, 139 and 188; Class 90 As Shown By Construction NOS. 83A, 93, 112, 113, 113A, 115, 119, 126, 127, 130, 139, 165, 178, 180, 185, 185A, 189, 198, 199, 210, 224, 227, 245, 246 and 291.

ALSO CLASSIFIED for use in all roof deck construction Classified for wind uplift resistance in which the metal roof deck panels (TJPV) are directly fastened to structural members (purlins, bar joints, etc.) by means of self-drilling or self-tapping screws, or similar fastening products. The length of the fasteners shall be a minimum of 3/4" in. longer than the nominal thickness of the rigid insulation, such that full thread engagement is assured. When insulation with thickness greater than 3 1/2" in. is used, steel washers used with panel-to-purlin screws are to be 5/8" in. OD minimum.

The insulation shall be installed as follows: Butt joints to occur over structural members. Top surface of the insulation at all joints may be continuously sealed with a minimum of 2 in. wide pressure-sensitive tape.

SEE UL Roofing Materials and Systems Directory.



Build On Our Knowledge™

Additional Information

Further information concerning the products, systems, and test methods described in this publication can be obtained by contacting Celotex Corporation, Tampa, or one of its Regional Sales Offices listed below.

The systems in this book are for illustration purposes only. The structural integrity of such systems is the responsibility of the design engineers, architects, component manufacturers, applicators and erectors.

WARNING:

Celotex® Thermax® products should be used only in strict accordance with Celotex Application Instructions. When Thermax products are used alone or used with non-combustible building components, they will burn if subjected to a fire of sufficient intensity, but will not contribute to the rapid spread of fire. Thermax products and other insulations, when used with exposed combustible materials may contribute to the rapid spread of fire.

All common building materials like wood and Thermax Insulation products release toxic smoke if ignited.

Thermax foil-faced products when applied in accordance with Celotex' instructions, meet requirements of the model building codes, various insurance authorities and other regulatory bodies in a wide variety of recommended applications.

Characteristics, properties or performance of materials manufactured by Celotex Corporation herein described are derived from data obtained under controlled test conditions. Celotex makes no warranties, express or implied, as to their characteristics, properties or performance under any variations from such conditions in actual construction. Celotex Corporation assumes no responsibility for the effects of structural movement.

ANY DEVIATION FROM THESE INSTRUCTIONS VOIDS ALL WARRANTIES, INCLUDING IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Thermax Insulation Board products are protected by one or more of the following U.S. Patents:

3,903,346	4,028,158	4,169,921	4,346,133
3,940,517	4,043,719	4,284,683	4,386,983
4,411,949	4,572,865	RE30984	

NOTICE: The information in this document is subject to change without notice. Celotex assumes no responsibility for any errors that may inadvertently appear in this document.

Celotex, and Thermax are registered trademarks of Celotex Corporation.



Build On Our Knowledge™

CELOTEX CORPORATION
POST OFFICE BOX 31602
TAMPA, FLORIDA 33631
www.celotex.com
1-800-CELOTEX

© Celotex Corporation

For Additional Information On Thermax (LD) Call:

REGIONAL SALES OFFICES

ATLANTA, GA

2700 Cumberland Parkway
Suite 550
Atlanta, Georgia 30339
Phone: (770) 436-6000
800-952-9978 Fax: (770) 438-8954

CHICAGO, IL

Touhy Office Plaza
1400 E. Touhy Avenue
Suite 225
Des Plaines, Illinois 60018
Phone: (847) 298-1929 or (847) 298-1943
800-851-6021 Fax: (847) 803-1246

CINCINNATI, OH

9403 Kenwood Road
Suite B201
Cincinnati, Ohio 45242
Phone: (513) 792-8210 or (513) 792-8250
800-543-8638 or 800-543-8676
Fax: (513) 792-8223

DALLAS, TX

13800 Monfort Drive
Suite 350
Dallas, Texas 75240-4384
Phone: (972) 661-1406 or (972) 404-0926
800-523-4684 or 800-356-9062
Fax: (972) 661-1835

OAKLAND, CA

6400 Stevenson Blvd.
Fremont, California 94538
Phone: (510) 490-0491 or (510) 656-7663
800-227-1216 or 800-227-0374
Fax: (510) 438-0271

PHILADELPHIA, PA

996 Old Eagle School Road
Wayne, Pennsylvania 19087
Phone: (610) 964-8047
800-556-4215 Fax: (610) 964-7924

MANUFACTURING PLANTS

1255 North 5th Street
Charleston, Illinois 61920
Phone: (217) 348-8151
800-637-2044 Fax: (217) 345-7741

1500 John Tipton Blvd.
Pennsauken, New Jersey 08110
Phone: (609) 663-2626
800-257-5313 Fax: (609) 663-1198

P.O. Box 5884
Texarkana, Arkansas 75505
Phone: (501) 774-3685
800-THERMAX Fax: (501) 772-5839

400 West Gandy Dancer Dr.
Tracy, California 95376
Phone: (209) 836-4440
800-992-8117 Fax: (209) 832-8944

EXPORT

Tampa, Florida 33631
Phone: (813) 873-4212
Fax: (813) 873-4287